
# | TECAWORK®



TECAWORK® BD 148 - 275/300 g/m<sup>2</sup>

## **MAXIMUM COMFORT**

This 100% cotton fabric feels naturally soft and ensures great wearers' comfort with its excellent breathability and moisture absorption.

### INDUSTRIAL LAUNDERABLE

Well-suited for extensive industrial laundering.

### **DURABLE**

Engineered to design quality workwear.





TECHNICAL DATA	TECAWORK®	TEST METHOD
Quality	BD 148	
Width	152 cm (+2/-1 cm)	ISO 22198: 2006
Weight	275/300 g/m² (±5%)	ISO 3801: 1978
Composition	100% cotton	ISO 1833: 2020
Construction	3/1 twill s	ISO 3572: 1976
Available finishes	Sanforized	

Physical performance		
Tensile strength	1100 N x 650 N (±10%)	ISO 13934-1: 2013
Tear strength	25 N x 25 N (±10%)	NEN-EN-ISO 13937-1: 2000
Dimensional change	Max. ± 5 %	ISO 5077: 2007 After 5x cleaning cycles at 75 °C ISO 15797: 2018

Care labelling		
Domestic laundering	© <u>X</u> ⊙ P	NEN-EN-ISO 6330, 6N 60 °C: 2013
Industrial laundering	75 °C - ISO 15797 White: Colour:	Visit our website for the laundering recommendations www.tencatefabrics.com  Qualification label - ISO 30023

CERTIFICATION		
	OEKO-TEX® STANDARD 100, class II	Centexbel; 1803034

#### **COLOURS**

Indigo 47004

 Bianco
 Dimgray
 Darkness
 Deepsky

 00001
 37094
 57538
 37097

The colours shown are standard options available with a minimum order of 100 meters. This service program is subject to change. Please scan the QR code or visit <u>our website</u> for the latest overview of standard colours.



For any additional colours or specific colour combination requirements beyond this service, please contact your TenCate Protective Fabrics representative.

Ten Cate Protect B.V. is certified according:



Product certification:

 $\label{thically sourced cotton} Ethically sourced cotton available via these programs:$ 













All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.